Stickers International

www.stickersinternational.com

Technical Datasheet - Poly Labels

Polypropylene - Gloss White

Label material:
White, glossy, biaxially oriented polypropylene film with topcoat
Grammage: approx. 45 g/m² ISO 536
Caliper: approx. 60 µm ISO 534
Tensile stress MD: approx. 105 N/mm² ISO 527
Tensile stress CD: approx. 185 N/mm² ISO 527
Surface gloss (Angle: 60° to the perpendicular): approx. 90 % DIN EN ISO 2813
Opacity: approx. 85 % ISO 2471

Adhesive:
Permanent, transparent acrylic based adhesive
Tack: high
Peel adhesion: high
Shear: extremely high
Minimum application temperature: 0 °C
Service temperature: -30 °C to +80 °C

Release liner:
White, supercalendered glassine
Grammage: approx. 62 g/m² ISO 536
Caliper: approx. 54 µm ISO 534
Tensile strength MD: approx. 88 N/15 mm DIN 53112
Tensile strength CD: approx. 38 N/15 mm DIN 53112
Transparency: approx. 51 % DIN 53147

Direct application to food:
ISEGA certification for dry, damp, & fatty foodstuffs. (Correction factor 3)

Polypropylene - Matt White

Label material:
White, matt, polypropylene film with topcoat
Grammage: approx. 47 g/m² ISO 536
Caliper: approx. 65 µm ISO 534
Tensile stress MD: approx. 80 N/mm² ISO 527
Tensile stress CD: approx. 180 N/mm² ISO 527
Opacity: approx. 87 % ISO 2471

Adhesive:
Permanent, transparent acrylic based adhesive
Tack: high
Peel adhesion: high
Shear: extremely high
Minimum application temperature: 0 °C
Service temperature: -30 °C to +80 °C

Release liner:
White, supercalendered glassine
Grammage: approx. 62 g/m² ISO 536
Caliper: approx. 54 µm ISO 534
Tensile strength MD: approx. 88 N/15 mm DIN 53112
Tensile strength CD: approx. 38 N/15 mm DIN 53112
Transparency: approx. 51 % DIN 53147

Direct application to food:
ISEGA certification for dry, damp, & fatty foodstuffs. (Correction factor 3)

Disclaimer: Product performance should always be tested in the actual application conditions. We cannot assume any liability for damage caused through the use of our products as they are used in conditions beyond our control.